



F&D

O'CONNOR PTY LTD

Lightweight Conveyor Belting and Power Transmission Specialists

Daclon Belts



Daclon.

F&D

O'CONNOR PTY LTD

www.fdoconnor.com.au

15 PELMET CRESCENT
THOMASTOWN VIC 3074
AUSTRALIA

PHONE: (03) 9462 4544
FAX: (03) 9462 4744
EMAIL: belts@fdoconnor.com.au

www.fdoconnor.com.au

15 PELMET CRESCENT
THOMASTOWN VIC 3074
AUSTRALIA

PHONE: (03) 9462 4544
FAX: (03) 9462 4744
EMAIL: belts@fdoconnor.com.au

Daclon Belts

Daclon Belts

Thickness (mm)	0.9
Max Width (mm)	420
Min Pulley Diameter (mm)	12
Load for 1% Elongation (N/mm)	104
Recomended Pre-Tension	0.1% - 0.3%
Breaking Strength Per mm (N)	240
Hardness (ShA)	75
Belt Elongation (%) Per mm Endless at Tensile Force	30N 0.2 - 0.4%
	60N 0.5 - 0.7%
	100N 0.9 - 1.1%
Min Operating Temp (°C)	-20
Max Operating Temp (°C)	100
Tensile Element	Aramide
Cover/Coating	Polychloroprene
Colour	Black
Co-efficient of Friction (u)	0.6
Anti Static	Yes

Available Sizes

Daclon belts are manufactured endless and are available in lengths from 475mm to 2500mm in increments of 25mm (i.e. 475, 500, 525 etc.).



Daclon®